

### REMARKS

Applicants have replaced the abstract and amended the claims to improve the claim language and to eliminate improper claim dependency. Applicants have also amended the specification to correct some headings and to rearrange the specification in accordance with usual U.S. practice. The revisions to Table 2 correct obvious typographical errors in identifying the examples tested. Applicants attach a clean copy of the application as amended above in the third Appendix . No new matter has been added, nor has the claim scope been narrowed by these amendments.

Early action allowing claims 1-9 is solicited.

In the event that the transmittal letter is separated from this document and the Patent and Trademark Office determines that an extension and/or other relief is required, applicant petitions for any required relief including extensions of time and authorizes the Commissioner to charge the cost of such petitions and/or other fees due in connection with the filing of this document to **Deposit Account No. 03-1952** referencing docket no. 358362011400.

Respectfully submitted,

Dated: September 18, 2006

By:



Barry E. Bretschneider  
Registration No. 28,055

Morrison & Foerster LLP  
1650 Tysons Boulevard, Suite 300  
McLean, Virginia 22102  
Telephone: (703) 760-7743  
Facsimile: (703) 760-7777

[0059]

Table 2

	swelling ratio		product takeout width X (mm)	thickness variation rate Y (%)	thermal shrinkage (%)			thermal shrinkage (%)			gloss (%)	Processing applica- bility	thickness variation rate Z (%)
	base layer	sealing layer			right end	Center	left end	right end	center	left end			
Ex. 3	1.31	1.24	6200	6.2	0.3	0.1	0.4	3.2	3.8	3.1	130	⊙	6.0
Ex. 4	1.31	1.24	6200	7.3	0.5	0.4	0.1	2.9	3.3	3.8	127	○	6.4
Comp. Ex. 3	1.31	1.47	6200	15.5	-0.1	0.1	0.4	3.2	2.2	1.2	120	×	24.7
Comp. Ex. 4	1.31	1.24	6200	20.0	1.0	0.7	0.5	2.5	4.1	3.6	115	×	26.3